



AMETA
SOLUTION

RUST-SAFE

70-37

PRODUCT TYPE

Primary corrosion protection on all blank metal surfaces.
Secondary corrosion protection on already existing rust-film (even advanced) by creating a tight barrier to air and water.

UTILISATION

Surfaces must be free from oil, grease, loose rust or any other substitutes.
Apply and allow drying for 12 to 24 hours before applying paint.
For heavy industrial use: apply two coats and for body shops: apply 1 coat.

AVANTAGES AND PROPERTIES

- Very appropriate in saline conditions. Ex: Sea water.
- 600 hours salt spray test to DIN 50.021.
- Excellent adhesion, also on rust.
- Quick drying after 10 minutes at 20°C.
- The coating is conductive and can be welded.
- Compatible with all paints and varnishes.
- No chemical reaction after application.
- UV stable.
- Stops penetration / migration of rust at incidental cuts.
- **Test certificate on corrosion protection according to DIN 53.210 and DIN 53.209. Results of salt spray test after, 150, 300, 400 and 600 hours and at coating thickness of 35, 58 and 70 um.**

RECOMMENDATIONS

Flammable.
Follow label instructions.

PACKAGING

<u>Description</u>	<u>Format</u>	<u>Product no.</u>
Spray	400 ml	70-37

3556, boul. des Entreprises
Terrebonne (QC) Canada J6X 4J8
1-888-452-6382 – (450) 477-3102
F (450) 477-6664

ametasolution.com